

Petrothene®

GA564189

Linear Low Density Polyethylene
Injection Molding Grade

Melt Index 21 Density 0.924

Applications

PETROTHENE GA564189 exhibits good stiffness and low temperature toughness. Typical applications include trash cans, industrial containers, housewares and toys.

Regulatory Status

GA564189 is currently being tested for suitability in FDA applications. Contact your Equistar sales representative for more information.

Processing Techniques

Specific recommendations for processing GA564189 can only be made when the processing conditions, equipment and end use are known. For further suggestions, please contact your Equistar sales representative.

Suggested Start-up Conditions

Extruder Zone	Rear	Center	Front	Nozzle
Cylinder Temperature °F (°C)	350 (177)	375 (190)	400 (204)	400 (204)

Typical Properties

Property	Nominal Value	Units	Test Method
Melt Index	21	g/10 min	ASTM D 1238
Density	0.924	g/cc	ASTM D 1505
Spiral Flow ¹	12.9 (32.8)	in (cm)	Equistar
Tensile Strength @ Break	1,200 (8)	psi (MPa)	ASTM D 638
Tensile Strength @ Yield ²	2,000 (14)	psi (MPa)	ASTM D 638
Elongation @ Yield ²	12	%	ASTM D 638
1% Secant Modulus ³	55,000 (380)	psi (MPa)	ASTM D 790
2% Secant Modulus ³	46,000 (320)	psi (MPa)	ASTM D 790
Vicat Softening Point	205 (96)	°F (°C)	ASTM D 1525
Hardness, Shore D	53		ASTM D 2240
Heat Deflection Temperature, 66 psi ⁴	117 (47)	°F (°C)	ASTM D 648
Low Temperature Brittleness, F ₅₀ ⁵	< -105 (<-76)	°F (°C)	ASTM D 746

¹ Measures the number on inches of flow produced when molten resin is injected into a long, spiral channel (0.625" insert), at a constant injection pressure of 1,000 psi with a melt temperature of 440°F.

² Crosshead speed - 20 in/ min

³ Crosshead speed - 1/2 in/ min

⁴ Data is for control and development work and not intended for use in design or predicting endurance at elevated temperatures.

⁵ Test method has been found useful for specification purposes, but does not necessarily indicate the lowest temperature at which the material may be used.

The information on this document is, to our knowledge, true and accurate. However, since the particular uses and the actual conditions of use of our products are beyond our control, establishing satisfactory performance of our products for the intended application is the customer's sole responsibility. All uses of Equistar products and any written or oral information, suggestions or technical advice from Equistar are without warranty, express or implied, and are not an inducement to use any process or product in conflict with any patent.

Equistar materials are not designed or manufactured for use in implantation in the human body or in contact with internal body fluids or tissues. Equistar makes no representation, promise, express warranty or implied warranty concerning the suitability of these materials for use in implantation in the human body or in contact with internal body tissues or fluids.

More detailed safety and disposal information on our products is contained in the Material Safety Data Sheet (MSDS). All users of our products are urged to retain and use the MSDS. A MSDS is automatically distributed upon purchase/order execution. You may request an advance or replacement copy by calling our MSDS Hotline at 800.700.0946.

® Petrothene is a registered trademark of Equistar Chemicals, LP.



Lyondell Chemical Company
1221 McKinney, Suite 700
P.O. Box 2583
Houston, Texas 77252-2583
800.615.8999
<http://www.Lyondell.com>